

RANDOGRIP 100

GENERAL INFORMATION	PHYSICAL PROPERTIES	APPLICATION
<p>Randogrip 100 is a one component modified epoxy anti slip floor and deck coating engineered to resist heavy pedestrian traffic.</p> <p>Randogrip 100 is easy to apply and offers excellent adhesion to concrete, wood and metal surfaces.</p> <p>Randogrip 100 resists oil, gasoline, acids, caustics and most solvents.</p> <p>Randogrip 100 has been formulated to meet the strict requirements of South Coast Air Quality Management District Rule 1113.</p> <p>Randogrip 100 is economical to use since it is a one component product and can be resealed for later use.</p> <p>Randogrip 100 is USDA approvable.</p> <p>Randolph Products Co. warrants that its products meet its internal specifications and are of merchantable quality. However, the purchaser is solely responsible for the suitability of the product for any particular application. The purchaser should thoroughly test or qualify the product for serviceability, environmental compliance and health and safety factors prior to use. Further, our total liability is limited to the price of the product or replacement in kind.</p> <p>Randolph Products Company 33 Haynes Circle Chicopee, MA 01020 Phone: 413-592-4191 Fax: 413-594-7321 www.randolphproducts.com</p>	<ol style="list-style-type: none"> 1. Colors: Medium Gray – 600D09 Black – 600K06 Tile Red – 600R02 Tan – 600T01 Safety Yellow – 600Y03 2. Solids by Volume: 62 +/- 2% 3. VOC content: 2.07 lbs/gallon (248 grams/liter) 4. Dry Time @ 70°F (21°C): For Light Traffic: 12 hours For Heavy Traffic: 72 hours Full Cure: 7 – 10 days 5. Coefficient of Friction: Dry: 1.2 Wet: 1.0 6. Theoretical Coverage: 75 ft²/gallon (roller) 60 ft²/gallon (trowel) 90 ft²/gallon (sprayed) 7. Shelf Life: Two Years 	<p>Surface Preparation: Concrete: Remove oil, grease, dirt, or other surface contaminants using a commercial grade cleaner/degreaser. Flush the area with water to remove any residue and allow to dry. Remove any paint, laitance or loose concrete by scarification or blasting. Smooth or glazed surfaces should be roughened to improve adhesion. New concrete should be cured for at least 30 days prior to application. All release agents, hardeners or sealers must also be removed as they may interfere with adhesion. Prime the clean, dry surface with Randogrip WB Epoxy Surface Primer.</p> <p>Metal: All surfaces must be clean, dry and free of surface contamination. The surface should be prepared to a minimum Commercial Blast per SSPC-SP 6. Prime blasted surfaces immediately with Randogrip Metal Primer to prevent flash rust.</p> <p>Wood/Fiberglass: Remove oil, grease or other surface contaminants using a commercial grade cleaner/degreaser. Flush the area with water to remove any residues and allow to dry. Sand the surface to remove loose material and to create a surface profile for application. Prime wooden surfaces with Randogrip WB Epoxy Surface Primer. Prime fiberglass surfaces with Randogrip Metal Primer.</p> <p>Mixing: Mixing should be done with a mechanical mixer such as a pneumatic drill motor with a jiffy mixing blade until contents are a uniform color.</p> <p>Roller Application The best anti slip characteristics are obtained when the product is applied by roller. For best results, do not thin and apply using a phenolic core roller on even surfaces. On irregular surfaces use a bristle</p>

Randolph Products Company

33 Haynes Circle

Chicopee, MA 01020

Telephone 413-592-4191

Facsimile: 413-594-7321



core roller or short nap roller.
To roll, pour a strip of Randogrip 100 on the surface approximately 2 inches long and 6 inches wide. Roll by pulling the material toward you in slow straight strokes.
Use a modest amount of downward pressure on the roller. It is important that the rolled profile expose the maximum amount of nonslip aggregate. If the aggregate is not properly exposed, the coating may become slippery when wet. Make sure coating is even without any thick puddles. If the coating is too heavy, it may not dry properly.
Protect exterior applications from rain for at least 24 hours. High humidity will retard drying.
Apply at surface temperatures between 50°F and 120°F. Application below 50°F is not recommended.

Spray:

Spray:

Randogrip 100 can be sprayed using Mastic Spray Equipment. A minimum of a 5 gallon bottom outlet pressure pot equipped with a double regulator and air driven agitator with a 1" I.D. outlet pipe.
Use a maximum of 25 feet of 3/8" hose for air and a maximum of 25 feet of 3/4" hose for the material.
The Spray gun should be equipped with a 1/4" fluid nozzle and a 1/4" internal air cap. Minimum air supply is 20 CFM at 90 lbs. pressure.
Material pressure should be 15 – 20 psi.
Fluid pressure should be 20 – 25 psi.
Maintain constant agitation of the product to insure the aggregate does not settle out during application.
Spray at a distance of 16 – 24 inches from the surface.

Trowel:

Randogrip 100 may be applied with a smooth trowel such as a plasterer's finishing trowel. A trowel about 4 inches by 12 inches for best results. Pour a strip of Randogrip 100 on the surface approximately 2 inches long and 6 inches wide. Hold the trowel at a 45° angle to the

Randolph Products Company

33 Haynes Circle

Chicopee, MA 01020

Telephone 413-592-4191

Facsimile: 413-594-7321



		<p>surface and spread with a full motion. Reverse the angle of the trowel for an opposite stroke. Pull the material toward you to give the proper appearance.</p> <p>Surface Maintenance: Maintain a clean surface to ensure the maximum performance from the anti slip coating. The following cleaning procedure is recommended: Foreign matter such as chewing gum should be removed with a scraper or putty knife. Use an all purpose biodegradable cleaner/degreaser mixed with water to clean the surface. Scrub the surface with a long handled, fiber bristled brush or floor machine. Rinse with clean water and dry.</p> <p>Note: While Randogrip is extremely durable, it is not a permanent coating and will require occasional touch up, especially in heavy traffic areas.</p> <p>Safety Precautions: This product is intended for professional use in an industrial environment only. Consult the Material Safety Data Sheet prior to application.</p>
--	--	---