

MIL-DTL-53022D Epoxy Primer Coating – Type 1

GENERAL INFORMATION	PHYSICAL PROPERTIES	APPLICATION
<p>A two component lead and chromate free anticorrosive primer.</p> <p>Qualified under MIL-PRF-53022D Type 1.</p> <p>This product may be used as a primer under CARC coatings specified in MIL-DTL-53039 or MIL-DTL-64159, MIL-PRF-22750 epoxy topcoats or MIL-PRF-85285D (non aircraft) polyurethane topcoats.</p> <p>Randolph Products Co. warrants that its Products meet its internal specifications and are of merchantable quality. However, the purchaser is solely responsible for the Suitability of the product for any particular application. The purchaser should thoroughly test or qualify the product for serviceability, environmental compliance and health and safety factors prior to use. Further, our total liability is limited to the price of the product or replacement in kind.</p> <p>Randolph Products Company 33 Haynes Circle Chicopee, MA 01020 Phone: 413-592-4191 Fax: 413-594-7321 www.randolphproducts.com</p>	<ol style="list-style-type: none"> 1. Color: Lighter than Fed. Std. 26622 2. Volume Solids: 39.4 +/- 2% 3. Solids by Weight: 56.7 +/- 2% 4. Viscosity: 63 – 73 KU 5. DFT: 1.3 – 1.7 mils 6. Theoretical Coverage @ 1 mil dft: 632 ft²/gallon 7. Gloss @ 60° 10 – 30 8. Dry Time Set to Touch: 15 minutes max. Dry Hard: 1.5 hours max. Through Dry: 4 hours max. 9. Pot Life 8 hours maximum 10. Mix Ratio 4:1 by volume 4 parts Component A 1 part Component B 11. VOC 4.26 lbs/gallon (511 grams/liter) 	<p>Steel: Surface must be clean and free of grease, dirt, oil, rust and other contaminants that could interfere with proper adhesion. Pretreatment with TT-P-490E Type 1 or DOD-P-15328D Wash Primers will give the best adhesion and performance. When blasting the surface a minimum of SSPC-SP6 is required for best performance.</p> <p>Aluminum: Clean with an appropriate cleaner to remove contamination from the substrate. Pretreat the surface with a wash primer or other conversion coating.</p> <p>Galvanized and other metals: Clean and remove surface contamination including oxidation. Treat with a wash primer to improve adhesion to the substrate.</p> <p>Note: Due to wide variations in substrates, surface preparation etc. It is recommended that the customer check adhesion and compatibility.</p> <p>Reduction: Reduce with MIL-T-81772 Type 1 or Type 2 as required.</p> <p>Conventional Spray: Atomizing Pressure: 45 – 55 psi Pot Fluid Pressure: 10 – 20 lbs.</p> <p>Airless Spray: Tip Size: 0.015 – 0.021” orifice Atomizing Pressure: 2800 psi minimum</p> <p>Clean-up: Clean tools and equipment immediately after use with MEK, MAK or MIL-T-81772 Type 1 or 2 thinner.</p> <p>Safety Precautions: This product is intended for professional use in an industrial environment only. Consult the Material Safety Data Sheet prior to application.</p>